

# Noelson Chemicals

www.noelson.com

## Formulation Guideline Vinyl Ester Glass Flake Coating

### Guideline:

#### Part A

Product Name	Suggested Amount %
Vinyl ester resin	60.0-77.0
Noelson™ GF-120M/GF-180M (Glass flake)	20.0-30.0
Anti-setting agent	1.0-5.0
Degassing agent	0.1-2.0
Pigment	2.0-7.0
Cobalt naphthenate	0.5-1.0
Initiator	2.0

### Disclaimer:

The guideline is provided for informational purposes only.